



滤纸参数列表(丙烯酸树脂)

应用	型号	树脂含量 % ±2	定量 g/m² ±5	厚度 mm ±0.05	透气度 L/m².S ±10	最大孔径 μm (≥)	平均孔径 μm	挺度 mN.m (≥)	耐破度 Kpa (≥)	瓦楞深度 mm ±0.03	水分 ±1%
重型车 空气滤纸	CX7-WX	20	120	0.5	150	45	43	4.5	310	0.45	4
	CX9-WX	20	110	0.5	120	38	32	4.0	450	0.43	4
	CX8371AAA-WX	20	135	0.5	200	55	51	4.0	260	0.43	4
	CX9958A-WX	20	110	0.3	140	45	41	4.5	300	0.45	4
	K937A-800-PX	20	100	0.5	800	100	90	3.0	280	0	4
	K5293-WX	20	130	0.35	270	65	55	4.0	240	0.33	4
	K8371C-WX	20	135	0.5	200	60	54	4.0	260	0.43	4
	NX12-WX	20	110	0.4	140	41	38	4.0	395	0.45	4
	NX13-WX	20	110	0.4	140	38	34	4.1	450	0.45	4
	NX90755-WX	20	115	0.5	140	40	35	4.0	340	0.45	4
	NX930911A-WX	20	110	0.5	140	38	32	4.0	450	0.43	4
空气滤纸	K672-WX	20	125	0.5	530	85	75	3.5	240	0.33	4
	K917-PX	20	135	0.5	310	80	72	3.5	280	0	4
	K985-PX	20	125	0.5	370	80	72	3.5	280	0	4
	K6003-PX	20	125	0.5	380	80	72	3.5	280	0	4
	K6851-PX	20	125	0.5	340	80	74	3.5	220	0	4
集尘器 滤纸	K801-W	20	135	0.5	360	80	73	5.0	300	0.25	4
	K803-W	20	135	0.5	350	85	80	4.0	280	0.25	4
机油滤纸	J666-WX	20	145	0.55	350	80	75	4.0	260	0.33	4
	J8491D-WX	20	145	0.6	320	75	71	4.1	300	0.43	4
	J911-WX	20	200	0.6	400	78	73	10.0	400	0.35	4
旁通滤纸	P800T-P	5	260	0.8	70	50	45	10.0	450	0	4
	P8001T-P	5	290	0.8	90	50	45	10.0	450	0	4
燃油滤纸	R9112D-W/P	20	130	0.45	200	63	60	4.0	280	0.25	4
	R8091L-W/P	20	200	0.65	200	60	55	6.0	380	0.25/0	4
	R800G-W/P	20	150	0.5	150	55	50	5.0	320	0.25/0	4

备注：

1. 定量测试样本0.01m²，天平精度0.01g
2. 孔径测试采用冒泡法，第一个泡下压差查表得最大孔径
3. 透气度测试压差P=200mm水柱，孔板70cm²
4. 挺度样本宽度38mm，弯曲角度15°
5. 耐破度测试采用液压递增原理，膜厚0.86±0.06mm
6. 水份烘干法，温度105±2℃，至恒重

石家庄天锦晟无纺科技有限公司